

## Single component medium-weight concrete and masonry reinstatement mortar for use in hot climates

### Uses

Renderoc TG is suitable for hand application to repairs where light to medium load bearing is required. Typical applications would include, but not be limited to, the following:

- Vertical and overhead repairs to restore 'covercrete'
- General concrete and masonry repairs
- Voids greater than 10 mm deep
- Repairs to honeycombing
- Larger scale repairs where formwork cannot be erected

### Advantages

- High build achievable without formwork - saving time and expense of multiple applications
- Formulated for use in hot climates
- Can be applied by the wet or dry spray process for fast exceptionally high build repairs with enhanced characteristics
- Low permeability provides good protection against carbon dioxide and chlorides
- Excellent bond to concrete substrate
- Shrinkage compensated
- Contains no chloride admixtures

### Description

Renderoc TG is supplied as a ready to use blend of dry powders, which requires only the addition of clean water to produce a highly consistent, lightweight repair mortar suitable for general purpose concrete and masonry repairs.

### Properties

The following typical results were obtained at a water to powder ratio of 0.18 and temperature of 20°C.

Test method	Typical result
<b>Compressive strength</b> (BS 1881 Pt.116)	<b>Tolerance (±10%)</b> : 40 N/mm <sup>2</sup> at 7 days 50 N/mm <sup>2</sup> at 28 days
<b>Slant shear bond strength to concrete (BS 6319 Pt.4)</b>	: 25 N/mm <sup>2</sup> at 28 days
<b>Water absorption ISAT</b> (BS 1881 Pt. 5)	: 0.18 ml/m <sup>2</sup> /sec at 10 mins. 0.06 ml/m <sup>2</sup> /sec at 2 hours
<b>Coefficient of thermal exp.:</b>	: 7 to 12 x 10 <sup>-6</sup> /°C
<b>Setting times</b> (BS 5075)	: 2-3 hours - Initial set 4-6 hours - Final set
<b>Fresh wet density</b>	: 1850 kg/m <sup>3</sup>

**Note :** The low permeability of RenderocTG retards chemical attack in aggressive environments. The cured mortar is resistant to acid gases, chloride ions, oxygen and water. For specific data regarding chemical resistance, contact the local Fosroc office.

### Design criteria

Renderoc TG is designed for vertical, overhead or horizontal use without the use of formwork. Attention to the basic design criteria given below should ensure that the full benefits of this technology are gained in use :

(i) Recommended limits for a single application are:

Minimum applied thickness	: 10 mm
Large overhead sections	: up to 20 mm thick
Vertical sections	: up to 50 mm thick
Small pockets or horizontal	: up to 100 mm thick
Maximum length	: up to 3 m

(ii) In situations where a substrate/repair barrier is required, or enhanced bond strength/working time is required, or where the substrate is likely to be permanently wet or damp (e.g. seawalls, quays etc.), Nitobond EP epoxy bonding agent should be used.

(iii) Water addition = 4.5 ltrs / 25kg bag Under no circumstances should part bags be used or additional water be employed. Either of these two actions will adversely affect material performance, automatically invalidating Fosroc's standard product guarantee.

# Fosroc Renderoc TG

## Method Statement

Renderoc TG should be mixed and applied in strict accordance with the Product Method Statement, a copy of which may be obtained from your nearest Fosroc office.

## Estimating

### Supply

Renderoc TG	:	25kg bags
Nitobond AR*†	:	1 and 5 litres

### Yield

Renderoc TG	:	15.8 ltrs per 25kg bag
Nitobond AR*†	:	6-8m <sup>2</sup> /litre

## Limitations

- Renderoc TG should not be used when the ambient temperature is below 5°C and falling.
- Renderoc TG should not be part mixed.
- Renderoc TG should not be exposed to running water either during application or prior to final set.
- Water ponding is not recommended for curing.

## Storage

### Shelf life

Renderoc TG has a shelf life of 12 months; and Nitobond AR has a shelf life of 6 months, if kept in a dry environment, in its original, unopened packing. If stored in conditions of high humidity and/or temperature, the shelf life of Renderoc TG may be reduced to as little as 4 months.

## Precautions

### Health and safety

Renderoc TG contains cement powders which, when mixed with water or upon becoming damp, release alkalis which can be harmful to the skin.

During use, avoid inhalation of the dust and contact with the skin or eyes. Wear suitable protective clothing - eye protection, gloves and respiratory equipment (particularly in confined spaces).

The use of barrier creams to provide additional skin protection is also advised. In case of contact with the skin, rinse with plenty of clean water, then cleanse thoroughly with soap and water.

In case of contact with eyes, rinse immediately with plenty of clean water and seek medical advice. If swallowed seek medical attention immediately - do **not** induce vomiting.

### Fire

Renderoc TG and Nitobond AR are non-flammable and thus presents no fire hazard.

For further information, please refer to the Product Material Safety Data Sheets.

\* Denotes the trademark of Fosroc International Limited

† See separate data sheet



## Al Gurg Fosroc Co. LLC

Post Box 657, Dubai  
United Arab Emirates  
[www.fosroc.com](http://www.fosroc.com)

### Important note

Fosroc products are guaranteed against defective materials and manufacture and are sold subject to its standard Conditions for the Supply of Goods and Service. **All Fosroc datasheets are updated on a regular basis. It is the user's responsibility to obtain the latest version.**

### Head Office

telephone: (+9714) 2039699

fax: (+9714) 2859649

email: [agf@fosroc.com](mailto:agf@fosroc.com)

### Regional offices

Abu Dhabi, Al Gurg Fosroc  
Bahrain, YBA Kanoo  
Kuwait, Boodai  
Oman, Al Amana

telephone: 673 1779  
telephone: 17738200  
telephone: 4817618  
telephone: 24815080

fax: 673 1449  
fax: 17732828  
fax: 4832124  
fax: 24817554

email: [abudhabi@fosroc.com](mailto:abudhabi@fosroc.com)  
email: [bahrain@fosroc.com](mailto:bahrain@fosroc.com)  
email: [kuwait@fosroc.com](mailto:kuwait@fosroc.com)  
email: [oman@fosroc.com](mailto:oman@fosroc.com)

