

SikaTop® 107 Plus

Waterproofing Coating

Description	2-component, pre-dosed, ready for use waterproofing slurry based on resin modified cementitious material.
Uses	For external and internal waterproofing, crack sealing, on concrete, mortar, brickwork, steel in: <ul style="list-style-type: none"> ■ Toilets ■ Flat roofs ■ Water tanks
Advantages	SikaTop® 107 Plus provides the following beneficial properties: <ul style="list-style-type: none"> ■ Pre-dosed sets ■ Very easy to mix ■ Easy to use ■ Consistency can be chosen for application by brush or by trowel ■ Excellent adhesion on sound substrates ■ Impermeable ■ Good resistance to abrasion and erosion ■ No drying or shrinkage cracks if used according to instruction ■ Non-corrosive, non-flammable ■ Non toxic ■ Slightly flexible
Coverage	Depending on type of application, 2 coats always required 1 - 1.5 kg/m ² per coat
Instruction for Use	
Substrate Preparation	Concrete, mortar, brickwork: Sound, clean, free of oil, grease, dust or laitance, as even possible. <i>Absorbent substrates have to be thoroughly watered and must be damp wet prior to application of first coat of SikaTop® 107 Plus.</i>
Mixing	Pour half of component A (liquid) into mixing vessel. Add all component B (powder) and mix until you have slurry of uniform consistency.
Application	<i>By brush:</i> On vertical surface use suitable brush with synthetic bristles. On horizontal surface use rubber slide or push-broom.
Curing	Protect the freshly applied product against direct sunlight and strong winds. Use damp hessian or plastic sheet. Protect the applied SikaTop from rain and water splashes until fully hardened. (± 6 hours)
Limitation	<ul style="list-style-type: none"> ■ Do not use more than 2 kg/m² per coat ■ For roofing or other structures directly exposed to U.V light, it is suggested that SikaTop is protected with 2-3 cm of cement screed. ■ When required to provide a smooth and level surface, levelling screed or render shall be placed before the application of the waterproofing compound. It is recommended that bonding coat is used (e.g. Sikatop® 77 D: cement : sand = 1:2:1) before screeding. ■ If the substrate to which the SikaTop® 107 Plus is applied cannot dry, the polymer emulsion in it will not coalesce and the SikaTop® 107 Plus will not cure to a waterproof thin render. ■ For application of tile on top of SikaTop® 107 Plus, then Sikafix® Tile Adhesive should be used. For optimum result SikaFix Tile adhesive should be applied max. 48 hours after application of finish coat of SikaTop® 107 Plus (finish coat applied by brush).



Table of Contents

Technical Data

Form	A = Liquid	B = Powder
Colour	Concrete grey	
Density	1.9 – 2.0 kg/ ltr (part A + B mixed)	
Mixing Ratio	For brush application	1: 3 by weight
Pot life at 25 °C	Approximately 50 minutes	
Strength 28 days	Compressive Strength	222 kg/cm ²
	Flexural Strength	108 kg/cm ²
	Bond Strength	10.2 kg/cm ²
Shelf life	Minimum 12 months if stored in unopened original container.	
Storage	Dry, cool, shaded place	
Packaging	4 kg can	
Handling Precautions:	<ul style="list-style-type: none"> ■ Avoid contact with skin & eyes. ■ Wear protective gloves and eye protection during work ■ If skin contact occurs, wash skin thoroughly ■ If in eyes open and flood with warm water. Seek medical attention without delay. ■ A full Material Data Sheet is available from Sika on request. 	

Legal Notes

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the product when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.



PT. Sika Indonesia
 Jl. Raya Cibinong- Bekasi km. 20
 Limusunggal- Cileungsi
 BOGOR 16820 - Indonesia
 Tel. +62 21 8230025
 Fax +62 21 8230026
 Website : www.sika.co.id
[idn.sika.com](mailto:ikacare@id.sika.com)
 e-mail: sikacare@id.sika.com

Branches
 Surabaya :
 Komp. Pergudangan Meiko Abadi III Blok B-52 & B-53, Ds. Gemurung,
 Gedangan, Sidoarjo 61254
 Tel : 031-8911333; Fax : 031-8916333
 Medan :
 Jl. Serbaguna (Simp. Jalan Veteran), Kompleks Pergudangan Brayon
 Trade Center No. 34, Medan 20239
 Tel : 844 6697, 844 6997 ; Fax : (061) 844 6698
 Batam :
 Jl. Laksamana Bintan, Komp. Bumi Riau Makmur Blok E No.3, Sungai Panas
 Tel : (0778) 424928; Fax : (0778) 450189

